

# Braskem PE GM7040G

高密度聚乙烯

Braskem

## 产品说明

GM7040G is a High Density Polyethylene compound specially developed for the manufacturing of extruded pipes for gas pressurized line. It is produced with bimodal technology and has high molar mass. It shows high mechanical properties and has excellent resistance to hydrostatic pressure and stress cracking. The resin has MRS (Minimum Required Strength) of 8 MPa according to ISO 9080 and is classified as PE 80 according to ISO 12162. GM7040G is manufactured in yellow color and contains additives to protect it against ultraviolet radiation action and photodegradation.

Meets the requirements of NBR 14462:00 and ISO 4437:07.

Application:

Yellow PE 80 pressure pipes for gas distribution; jacketing of underwater cables.

## 供应商联系方式

上海松翰塑化科技有限公司

电话: 021-58958519

邮箱: sales@su-jiao.com

地址: 上海市奉贤区联合北路215号

## 基本信息

添加剂	紫外线稳定剂		
特性	高分子量	高密度	耐燃油性
用途	管道系统		
外观	黄色		
形式	粒子		
加工方法	管路挤出成型	挤出	

物理性能	额定值	单位制	测试方法
比重	0.947	g/cm <sup>3</sup>	ASTM D792
熔流率(熔体流动速率) (190°C/5.0 kg)	0.45	g/10 min	ASTM D1238
抗环境应力开裂 (50°C, 2.00 mm, 100% Igepal, 模压成型, F50)	> 1000	hr	ASTM D1693B
硬度	额定值	单位制	测试方法
肖氏硬度 (邵氏 D, 15 秒, 模压成型)	62		ASTM D2240
机械性能	额定值	单位制	测试方法
抗张强度			ASTM D638
屈服, 模压成型	23.0	MPa	ASTM D638
断裂, 模压成型	37.0	MPa	ASTM D638
伸长率			ASTM D638
屈服, 模压成型	9.2	%	ASTM D638
断裂, 模压成型	770	%	ASTM D638
弯曲模量 - 1% 正割 (模压成型)	1080	MPa	ASTM D790
冲击性能	额定值	单位制	测试方法
悬臂梁缺口冲击强度 (23°C, 模压成型)	240	J/m	ASTM D256
热性能	额定值	单位制	测试方法
载荷下热变形温度 (0.45 MPa, 未退火, 模压成型)	68.0	°C	ASTM D648
维卡软化温度	122	°C	ASTM D1525 <sup>1</sup>

## 备注

1. 压力1 (10N)