

Braskem PP H502-25RG

聚丙烯均聚物

Braskem Europe GmbH

产品说明

Braskem H502-25RG Polypropylene Resin is a homopolymer resin suitable for the use in spunbonded nonwovens production equipment. Braskem H502-25RG Polypropylene Resin can also be used in other Fiber spinning processes. Braskem H502-25RG Polypropylene Resin is a controlled rheology polypropylene offering excellent processability at melt temperatures between 220 and 280°C. Braskem H502-25RG Polypropylene Resin is modified to resist gas fading.

Applications for Braskem H502-25RG Polypropylene Resin:

Health and hygiene

Carpet face yarns

Geotextiles

Upholstery

Filtration

Agricultural materials

Protective clothing

Regulatory Information:

Braskem H502-25RG Polypropylene Resin should comply with EU, No 10/2011. It is the responsibility of the manufacturers of food contact articles and industrial food packers to make sure the articles in their actual use are in compliance with the imposed migration requirements. The appropriate regulations should be consulted for more detailed information. Compliance letters can be obtained through the Braskem sales representative.

供应商联系方式

上海松翰塑化科技有限公司

电话: 021-58958519

邮箱: sales@su-jiao.com

地址: 上海市奉贤区联合北路215号

基本信息

机构评级 欧洲 No 10/2011

形式 粒子

加工方法 纤维(纺纱)挤出

物理性能	额定值	单位制	测试方法
------	-----	-----	------

密度	0.900	g/cm ³	ISO 1183
----	-------	-------------------	----------

熔流率(熔体流动速率) (230°C/2.16 kg)	25	g/10 min	ISO 1133
-----------------------------	----	----------	----------

机械性能	额定值	单位制	测试方法
------	-----	-----	------

拉伸应力 (屈服, 注塑)	30.0	MPa	ISO 527-2
---------------	------	-----	-----------

拉伸应变 (屈服, 注塑)	10	%	ISO 527-2
---------------	----	---	-----------

弯曲模量 (注塑)	1300	MPa	ISO 178
-----------	------	-----	---------

冲击性能	额定值	单位制	测试方法
------	-----	-----	------

简支梁缺口冲击强度 (23°C, 注塑)	2.0	kJ/m ²	ISO 179/1eA
----------------------	-----	-------------------	-------------

热性能	额定值	单位制	测试方法
-----	-----	-----	------

热变形温度 (0.45 MPa, 未退火)	80.0	°C	ISO 75-2/B
-----------------------	------	----	------------

维卡软化温度	148	°C	ISO 306/A
--------	-----	----	-----------

挤出	额定值	单位制
----	-----	-----

熔体温度	220 到 280	°C
------	-----------	----